

EN Technical Data Sheet

Bectron[®]

SA 70L1-30

**Electronic 1 Part Neutral Cure
High Performance Silicone Adhesive**

ELANTAS Europe Sales offices:

Strada Antolini, 1
43044 Collecchio (PR)
Italy
Tel +39 0521 304777
Fax +39 0521 804410

Grossmannstrasse 105
20539 Hamburg
Germany
Tel +49 40 78946 0
Fax +49 40 78946 349

Via San Martino, 6
15028 Quattordio (AL)
Italy
Tel +39 0131 773870
Fax +39 0131 773875

Keate House
1 Scholar Green Road - Cobra Court
Manchester M32 0TR
United Kingdom
Tel +44 161 864 1689
Fax +44 161 864 6090

info.elantas.europe@altana.com
www.elantas.com/Europe

Area of application

Assembly of electrical and electronic equipments, lighting, sealing and bonding of corrosion sensitive devices.

Processing methods

Pre-treatment: Parts to be sealed should be clean dry and free from grease.

Bectron® SA 70L1-30 can be applied manually or using automatic dosing/dispensing systems

Description

Bectron® SA 70P1-15, is 1 part condensation cure products (Alkoxy) with low modulus and non corrosive when in contact with sensitive electronic parts. It also provides very good dielectric properties and have excellent adhesion to most common substrates used in the electronic industry

They are an ideal option for many electronic and lighting applications where high performance is a must.

Key Properties:

- Neutral cure
- Good dielectric properties
- Self Levelling
- Good adhesion to many substrates
- Temperature resistance from -55°C up to 200°C

Curing

Following exposure to atmospheric moisture the product will start to cure to a durable silicone elastomer. Full cure will depend on the relative humidity and ambient temperature. At 25°C and 55% Relative Humidity a 3mm section will normally cure in less than 24 hours. The volatile by-products of the curing system are relatively inoffensive alcohols (See Health and Safety Data).

Full bond strength and physical properties will be achieved after 5 days. Cure time depends on the thickness of the adhesive applied and shape of the surface exposed to the atmosphere.

It is recommended that a minimum thickness of 1 mm is achieved between parts to obtain best adhesion to substrates.

Storage and stability

Product should be stored in its original sealed container to avoid any potential contamination at a temperature below 35°C . Store accordingly to any specific instruction listed on the product label. Product should be used prior to the expiring date marked on the label

Handling precautions

The product is RoHS compliant. Refer to the safety data sheet and comply with local regulations relating to industrial health and waste disposal

SYSTEM SPECIFICATIONS

Property	Conditions	Method	Value	Units
Appearance	23°C	Visual	Translucent medium viscosity liquid free from visible impurities	---
Cure Time	23°C/55% RH	3 mm thickness	< 24	hours
Hardness	23°C	DIN 53505	>15	Shore A

TYPICAL PRODUCT CHARACTERISTICS

Property	Value
Colour	Translucent
Viscosity [mPas]	44000
Spec. gravity [g/cm ³]	1.05
Tack Free Time [min]	11*
Shelf Life [months]	12

* measured at 23°C and 55% relative humidity.

TYPICAL MECHANICAL PROPERTIES OF THE CURED PRODUCT

Property	Value
Tensile Strength [MPa]	1.05
Elongation at Break [%]	240

TYPICAL THERMAL PROPERTIES OF THE CURED PRODUCT

Property	Value
Thermal Conductivity [W/mK]	0.20
UL 94 Classification (Internal)	HB

TYPICAL DIELECTRIC PROPERTIES OF THE CURED PRODUCT

Property	Value
Volume Resistivity [$\Omega \cdot \text{cm}$]	$6.2 \cdot 10^{15}$
Dielectric Constant 60 Hz	2.60
Dielectric Dissipation 60 Hz	0.003
Dielectric Strength [KV/mm]	>18

Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition.